

## FRESCOLORI® scrape

Delivery and servicing surfaces exclusively by trained FRESCOLORI® processing specialists, with a long-term guarantee of high quality.

Hand-drawn longitudinal lines characterize the appearance of this surface and give it a harmonious appearance. Matte and glossy lines alternate playfully. The surface scrape combines vitality and tranquillity in a coherent manner.

Material: 3 CM1 layers

1 CM1.5 layer 2 wax layers

Consumption: 1. CM1 layer, about 0.2 kg/m2

CM1,5 layer, about 0.8 kg/m2
CM1 layer, about 0.12 kg/m2
CM1 layer, about 0.12 kg/m2
CM1 layer, about 0.12 kg/m2

Wax, about 0.08 kg/m2

Colour: freely selectable

Application: Indoor

Surfaces are prepared and primed.

- Application of the first layer of the Caramor limestone-marble plaster, in grain thickness 1, coverage application
- Observe the waiting times, with a rest period until the first layer is dry.
- Application of the second layer of the Caramor limestone-marble plaster, in grain thickness 1.5, thick and textured with wallpaper wipers
- Observe the waiting times, with a rest period until the second layer is dry.
- Application of the third layer of the Caramor limestone-marble plaster, in grain thickness 1, filling in the structural direction
- Observe the waiting times, with a rest period until the third layer is dry.
- Application of the fourth layer of the Caramor limestone-marble plaster, in grain thickness 1, filling in the structural direction
- Observe the quite short waiting time (less than touch dry)
- Application of the fifth layer of the Caramor limestone-marble plaster, in grain thickness 1, filling in the structural direction
- Polish the surface with a trowel
- Observe the waiting times, with a rest period until the fifth layer is dry.
- Carefully sand the corners and edges the next day
- Apply the first layer of wax with a trowel
- Apply the second layer of wax, if necessary, with a cotton cloth
- Polish the surface with a polishing machine provided with a lambskin covered disc